

# TITAN BLITZ | TBW-100

High tack gloss white print vinyl developed for shorter term applications on powervehicles. Combine with our lamination film TITAN LAM 250 GLOSS.

#### **FACE FILM**

Monomeric PVC, gloss white

| Thickness (µm)           | 100  |                |  |
|--------------------------|------|----------------|--|
| Tensile strength (N/mm²) | >58  | DIN EN ISO 527 |  |
| Elongation at break (%)  | >170 | DIN EN ISO 527 |  |

#### **ADHESIVE**

Clear solvent-based acrylic, high tack permanent

| Thickness (µm)           | 25          |  |
|--------------------------|-------------|--|
| Adhesion to steel        | FINAT FTM 1 |  |
| 20 minutes (180°) N/25mm | 21          |  |
| 24 hours (180°) N/25mm   | 28          |  |

# **RELEASE LINER**

Lay-flat kraft paper liner, double-sided PE-coated

Weight (gsm) 140

# PRODUCT APPLICATION

| Dimensional stability (.mm)  | <1,2      | FINAT FTM 14 |
|------------------------------|-----------|--------------|
| Application temperature (°C) | 10 to 25  |              |
| Service temperature (°C)     | -10 to 70 |              |

# **DURABILITY**

| Outdoor durability (years) | 3 | Northern-EU climate, vertical |
|----------------------------|---|-------------------------------|
|                            |   | exposure                      |

### **ROLL SIZES**

### **PRINTING METHOD**

1370mm x 50m (Eco)-Solvent, Latex, UV

Fourbases BV guarantees the material for twelve months from the date of final invoice. The shelf life of our material depends on storage conditions. The end user should store the material in the original boxes or in equivalent boxes, away from direct sunlight, at a temperature of 21°C and 50% relative humidity. Fourbases BV guarantees that the products are free from defects in workmanship or defects in TITAN material, provided they are stored properly. At its sole discretion, Fourbases BV may either: (1) replace all or part of the materials, or (2) issue a credit note for the value of the defective portion. All quoted data values are typical and should not be used as a basis to consider the product defective if measured values differ.